

**Amendments to the Claims:**

This listing of claims will replace all prior versions, and listings, of claims in the application:

**Listing of Claims:**

1. (Currently amended) An article comprising

(1) a first component composed of a first polymeric composition, the first polymeric composition comprising a side chain crystalline polymer which has

(a) a peak melting temperature  $T_p$  which is -20 to 40°C at least -40°C and at most 100°C,

(b) an onset of melting temperature  $T_o$  such that  $(T_p - T_o)$  is less than  $(-1.7757e^{-5}) \times (T_p^3) + (3.339e^{-3}) \times (T_p^2) - (6.977e^{-2}) \times (T_p) + k$ , where  $k$  is 16 to 24, and

(c) a heat of fusion of at least 5 J/g;

and

(2) a second component which

(a) is composed of a second composition, and

(b) overlaps the first component;

the first polymeric composition having a volume expansion between  $T_o$  and  $T_p$  which is greater than the volume expansion of the second composition over the same temperature range, and the first and second components having dimensions and shapes such that the article, in the absence of external restraint, changes shape when it is heated from  $T_o$  to  $T_p$  and when it is cooled from  $T_p$  to  $T_o$ .

2. (Original) An article according to claim 1 wherein the first polymeric composition has a volume expansion between  $T_o$  and  $T_p$  which is at least 5 times the volume expansion of the second composition over the same temperature range.

3. (Original) An article according to claim 1 wherein the first polymeric composition has a volume expansion between  $T_o$  and  $T_p$  which is 3 to 10 times the volume expansion of the second composition over the same temperature range.
4. (Currently amended) An article according to claim 1 wherein the first polymeric composition contains at least 80% of the side chain crystalline polymer.
5. (Canceled)
6. (Currently amended) An article according to claim 1 wherein the crystalline polymer is a side chain crystalline (SCC) polymer having a  $T_p$  of 20 to 40 °C, and a  $T_o$  such that  $(T_p - T_o)$  is less than  $(-1.7757e^{-5}) \times (T_p^3) + (3.339e^{-3}) \times (T_p^2) - (6.977e^{-2}) \times (T_p) + k$ , where k is 11.
7. (Currently amended) An article according to claim 1 wherein the first polymeric composition contains at least two said side chain crystalline polymers having  $T_p$ s which differ by a least 10 °C.
8. (Original) An article according to claim 1 which is a fiber which is relatively straight at temperatures above  $T_p$  and becomes curved when cooled from a temperature above  $T_p$  to a temperature below  $T_o$ .
9. (Original) An article according to claim 8 wherein the first and second components are in a configuration selected from side-by-side configurations and eccentric core-sheath configurations.
10. (Original) An article according to claim 8 which is a continuous filament having a constant cross section throughout its length.
11. (Original) A yarn comprising a fiber as defined in claim 8.

12. (Currently amended) A fibrous mass comprising a plurality of fibers each of which comprises

a first component composed of a first polymeric composition, the first polymeric composition comprising a side chain crystalline polymer which has

- (a) a peak melting temperature  $T_p$  which is -20 to 40°C ~~at least -40°C and at most 100°C~~,
- (b) an onset of melting temperature  $T_o$  such that  $(T_p - T_o)$  is less than  $(-1.7757e^{-5})(T_p^3) + (3.339e^{-3})(T_p^2) - (6.977e^{-2})(T_p) + k$ , where  $k$  is 16, and
- (c) a heat of fusion of at least 5 J/g;

and

a second component which

- (a) is composed of a second polymeric composition, and
- (b) overlaps the first component;

the first polymeric composition having a volume expansion between  $T_o$  and  $T_p$  which is at least 5 times greater than the volume expansion of the second composition over the same temperature range, and the first and second components having dimensions and shapes such that the fibrous mass article, in the absence of external restraint, changes shape when it is heated from  $T_o$  to  $T_p$  and when it is cooled from  $T_p$  to  $T_o$ .

13. (Canceled)

14. (Currently amended) A fibrous mass according to claim 12 wherein the first polymeric composition contains at least 80% of the side chain crystalline polymer, ~~and the crystalline polymer is a side chain crystalline (SCC) polymer having a  $T_p$  of -20 to 40 °C, and a  $T_o$  such that  $(T_p - T_o)$  is less than  $(-1.7757e^{-5})(T_p^3) + (3.339e^{-3})(T_p^2) - (6.977e^{-2})(T_p) + k$ , where  $k$  is 16.~~

15. (Original) A fibrous mass according to claim 12 wherein the fibers are relatively straight at temperatures above  $T_p$  and becomes curved when cooled from a temperature above  $T_p$  to a temperature below  $T_o$ .
16. (Original) A fibrous mass according to claim 15 wherein the first and second components are in a side-by-side configuration.
17. (Currently amended) A fibrous mass according to claim 12 wherein the side chain crystalline polymer is cross-linked.
18. (Original) A fibrous mass according to claim 12 which contains 10 to 50% of said fibers and 90 to 50% of other fibers.
19. (Original) A fibrous mass according to claim 12 which is part of clothing for a human being.
20. (Original) A method of making an article as defined in claim 1 which comprises coextruding first and second polymeric compositions as defined in claim 1.